

# CYCOLACT™ RESIN INP108

REGION AMERICAS

## DESCRIPTION

ABS, powder, medium impact. FDA compliant (part use must be at room temperature or below).

## TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Hardness, Shore D	58	-	ISO 868
<b>PHYSICAL</b>			
Specific Gravity	1	-	ASTM D 792
Density (Molded)	1.01	g/cm <sup>3</sup>	ISO 1183
Mean Resin Particle Size	400	micrometer	SABIC method
Total NA Volatiles	0.1	%	SABIC method
Rubber	32	%	SABIC method
Bulk Density	0.35	g/cm <sup>3</sup>	ASTM D 1895

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.