

CYCOLACT™ RESIN INPBMAT

REGION AMERICAS

DESCRIPTION

Cross-linked SAN in styrenic matrix. Provides excellent gloss reduction properties. Maintains original polymer properties such as impact etc. Compatible with various polymer such as PVC and ABS. Can be used in low gloss ABS products at typical loading around 5PHR. Can be effectively compounded with ABS and other styrenic thermoplastics in molded, extruded or calendered applications to provide excellent gloss reduction properties without losing other physical performance.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Flexural Stress, yld, 1.3 mm/min, 50 mm span	33	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	3700	MPa	ASTM D 790
Flexural Stress, yield, 2 mm/min	38	MPa	ISO 178
Flexural Modulus, 2 mm/min	3400	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	18	J/m	ASTM D 256
Izod Impact, notched 80*10*4 +23°C	2	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	1	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	94	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	86	°C	ASTM D 648
Vicat Softening Temp, Rate B/50	100	°C	ISO 306
Vicat Softening Temp, Rate B/120	102	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	87	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.07	-	ASTM D 792
Density	1.07	g/cm ³	ISO 1183
Melt Flow Rate, 220°C/10.0 kg	0	g/10 min	ISO 1133

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.