

## FORTRON® 6345L4 - PPS

### Description

Fortron 6345L4 is 30% glass fiber/high PTFE reinforced injection molding grade. This grade, available in natural and black color, exhibits improved wear and sliding properties versus 1342L4 product.


Physical properties	Value	Unit	Test Standard
Density	1660	kg/m <sup>3</sup>	ISO 1183
Molding shrinkage, parallel	0,3 - 0,5	%	ISO 294-4, 2577
Molding shrinkage, normal	0,6 - 0,9	%	ISO 294-4, 2577
Humidity absorption, 23 °C/50%RH	0,02	%	ISO 62

Mechanical properties	Value	Unit	Test Standard
Tensile stress at break, 5mm/min	150	MPa	ISO 527-2/1A
Tensile strain at break, 5mm/min	1,9	%	ISO 527-2/1A
Flexural modulus, 23 °C	10600	MPa	ISO 178
Flexural strength, 23 °C	230	MPa	ISO 178
Izod impact notched, 23 °C	9	kJ/m <sup>2</sup>	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
DTUL at 1.8 MPa	260	°C	ISO 75-1, -2
DTUL at 8.0 MPa	190	°C	ISO 75-1, -2

### Diagrams

#### True Stress-strain



#### Typical injection moulding processing conditions

Pre Drying	Value	Unit	Test Standard
Necessary low maximum residual moisture content	0,02	%	-
Drying time	3 - 4	h	-
Drying temperature	130 - 140	°C	-
Temperature	Value	Unit	Test Standard
Hopper temperature	20 - 30	°C	-
Feeding zone temperature	60 - 80	°C	-
Zone1 temperature	290 - 300	°C	-
Zone2 temperature	310 - 320	°C	-
Zone3 temperature	330 - 340	°C	-
Zone4 temperature	330 - 340	°C	-
Nozzle temperature	310 - 330	°C	-
Melt temperature	330 - 340	°C	-
Mold temperature	140 - 160	°C	-
Hot runner temperature	330 - 340	°C	-
Pressure	Value	Unit	Test Standard
Back pressure max.	30	bar	-
Speed	Value	Unit	Test Standard
Injection speed	fast	-	-

---

## FORTRON® 6345L4 - PPS

---

Screw Speed	Value	Unit	Test Standard
Screw speed diameter, 25mm	120	RPM	-
Screw speed diameter, 40mm	75	RPM	-
Screw speed diameter, 55mm	50	RPM	-

---

### Other text information

---

#### Pre-drying

FORTRON should in principle be predried. Because of the necessary low maximum residual moisture content the use of dry air dryers is recommended. The dew point should be  $\leq -30^{\circ}\text{C}$ . The time between drying and processing should be as short as possible.

---

#### Longer pre-drying times/storage

For subsequent storage the material should be stored dry in the dryer until processed ( $\leq 60$  h).

---

### Characteristics

---

---

#### Product Categories

Specialty

---

#### Contact Information

---

##### Americas

8040 Dixie Highway  
Florence, KY 41042 USA  
Product Information Service  
t: +1-800-833-4882  
t: +1-859-372-3244  
Customer Service  
t: +1-800-526-4960  
t: +1-859-372-3214  
e: info-engineeredmaterials-am@celanese.com

##### Asia

4560 Jinke Road  
Zhang Jiang Hi Tech Park  
Shanghai 201203 PRC  
Customer Service  
t: +86 21 3861 9266  
f: +86 21 3861 9599  
e: info-engineeredmaterials-  
asia@celanese.com

##### Europe

Am Unisys-Park 1  
65843 Sulzbach, Germany  
Product Information Service  
t: +49-800-86427-531  
t: +49-(0)-69-45009-1011  
e: info-engineeredmaterials-eu@celanese.com

---

### General Disclaimer

---

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values. Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products. The products mentioned herein are not intended for use in medical or dental implants.

---

### Trademark

---

© 2014 Celanese or its affiliates. All rights reserved. (Published 27.July.2016). Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC.