

iq.ul.com

PROSPECTOR®

View additional material information including performance and processing data

CLICK TO CONTINUE

The information presented on the UL Prospector datasheet was acquired by UL Prospector from the producer of the material. UL Prospector makes substantial efforts to assure the accuracy of this data. However, UL Prospector assumes no responsibility for the data values and strongly encourages that upon final material selection, data points are validated with the material supplier.

E41938

Component - Plastics

Guide Information

E I DUPONT DE NEMOURS & CO INC

ENGINEERING POLYMERS, CHESTNUT RUN PLAZA, PO BOX 80713, WILMINGTON DE 19880-0713

SK605

Polybutylene Terephthalate (PBT), glass reinforced "Crastin", furnished as pellets

Color	Min. Thk (mm)	Flame Class	HWI	HA1	RTI Elec	RTI Imp	RTI Str
ALL	0.75	HB	-	-	130	130	130
	1.5	HB	3	1	130	130	130
	3.0	HB	2	0	130	130	130
	6.0	HB	0	0	130	130	130
Comparative Tracking Index (CTI): 1				Inclined Plane Tracking (IPT) kV: -			
Dielectric Strength (kV/mm): 33				Volume Resistivity (10 ^x ohm-cm): -			
High-Voltage Arc Tracking Rate (HVTR): 1				Surface Resistivity (10 ^x ohms/square): -			
Dimensional Stability (%): 0				High Volt, Low Current Arc Resis (D495): 5			

NOTE - (1) Material designations that are color pigmented may be followed by suffix letters and numbers. (2) Material designations may be prefixed by "ZYT" for Zytel or "MIN" for Minlon or "DEL" for Delrin or "CRA" for Crastin or "RYN" for Rynite or "ETPV" for ETPV or "SOR" for Sorona grades.

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 1996-01-17

Last Revised: 2019-01-03

© 2020 UL LLC



IEC and ISO Test Methods				
Test Name	Test Method	Units	Thk (mm)	Value
Flammability	IEC 60695-11-10	Class (color)	0.75	HB, HB75 (ALL)
			1.5	HB, HB75 (ALL)
			3.0	HB, HB40 (ALL)
			6.0	HB, HB40 (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	°C	0.75	725
			1.5	725
			3.0	825
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	°C	0.75	750
			1.5	750
			3.0	800
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	°C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	°C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m ²	-	-
ISO Izod Impact	ISO 180	kJ/m ²	-	-
ISO Charpy Impact	ISO 179-1	kJ/m ²	-	-