The information presented on the UL Prospector datasheet was acquired by UL Prospector from the

producer of the material. UL Prospector makes substantial efforts to assure the accuracy of this data.

However, UL Prospector assumes no responsibility for the data values and strongly encourages that upon final material selection, data points are validated with the material supplier. E121562

iq.ul.com

PROSPECTOR® CLICK TO CONTINUE View additional material information including performance and

processing data Component - Plastics

Guide Information

SABIC INNOVATIVE PLASTICS US L L C

AMERICAS - RESIN, 1 PLASTICS AVE, PITTSFIELD MA 01201-3662

MG38U(GG) (f1)

Acrylonitrile Butadiene Styrene (ABS) "Cycolac", furnished as pellets

<u>Color</u>	<u>Min. Thk</u> (<u>mm)</u>	<u>Flame</u> <u>Class</u>	<u>HWI</u>	<u>HAI</u>	<u>RTI</u> <u>Elec</u>	<u>RTI</u> Imp	<u>RTI</u> <u>Str</u>
ALL	1.5	HB	-	-	60	60	60
	3.0	HB	-	-	60	60	60
Comparative Tracking Index (CTI): - Dielectric Strength (kV/mm): -			Inclined Plane Tracking (IPT) kV: - Volume Resistivity (10 ^x ohm-cm): -				
High-Voltage Arc Tracking Rate (HVTR): - Dimensional Stability (%): -			Surface Resistivity (10 ^x ohms/square): - High Volt, Low Current Arc Resis (D495): -				

(GG) - Denotes a global grade formulation previously in File E161759.

(f1) - Suitable for outdoor use with respect to exposure to Ultraviolet Light, Water Exposure and Immersion in accordance with UL 746C.

NOTE - Material designation may be followed by a color nomenclature consisting of either an alpha/numeric or numeric/alpha combination.

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

© 2020 UL LLC

Report Date: 1983-07-13 Last Revised: 2015-10-20

IEC and ISO Test Methods					
Test Name	Test Method	Units	Thk (mm)	Value	
Flammability	IEC 60695-11-10	Class (color)	1.5	HB, HB75 (ALL)	
			3.0	HB, HB40 (ALL)	
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	°C	-	-	
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	°C	-	-	
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-	
IEC Ball Pressure	IEC 60695-10-2	°C	-	-	
ISO Heat Deflection (1.80 MPa)	ISO 75-2	°C	-	-	
ISO Tensile Strength	ISO 527-2	MPa	-	-	
ISO Flexural Strength	ISO 178	MPa	-	-	
ISO Tensile Impact	ISO 8256	kJ/m ²	-	-	
ISO Izod Impact	ISO 180	kJ/m ²	4.0	8.9	
ISO Charpy Impact	ISO 179-1	kJ/m ²	-	-	