

LCY CHEMICAL CORP
3 Zhonglin Rd, Xiaogang District, Kaohsiung 812 TW

7523, 7533, EP332K, 7633, EP332H
Polypropylene (PP), furnished as pellets

| Color | Min. Thk (mm) | Flame Class | HWI | HA1 | RTI Elec | RTI Imp | RTI Str |
|-------|------------------|----------------|-----|-----|-------------|------------|------------|
| ALL | 1.5 | HB | 0 | 3 | 115 | 115 | 115 |
| | 3.0 | HB | 0 | 3 | 115 | 115 | 115 |

Comparative Tracking Index (CTI): 1

Dielectric Strength (kV/mm): 32

High-Voltage Arc Tracking Rate (HVTR): 0

Dimensional Stability (%): 0

Inclined Plane Tracking (IPT) kV: -

Volume Resistivity (10^x ohm-cm): 15

Surface Resistivity (10^x ohms/square): -

High Volt, Low Current Arc Resis (D495): 5

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 1983-12-28

Last Revised: 2013-07-31

© 2020 UL LLC



| IEC and ISO Test Methods | | | | |
|--------------------------------|-----------------|-------------------|----------|----------------|
| Test Name | Test Method | Units | Thk (mm) | Value |
| Flammability | IEC 60695-11-10 | Class (color) | 1.5 | HB, HB75 (ALL) |
| | | | 3.0 | HB, HB40 (ALL) |
| Glow-Wire Flammability (GWFI) | IEC 60695-2-12 | °C | - | - |
| Glow-Wire Ignition (GWIT) | IEC 60695-2-13 | °C | - | - |
| IEC Comparative Tracking Index | IEC 60112 | Volts (Max) | - | - |
| IEC Ball Pressure | IEC 60695-10-2 | °C | - | - |
| ISO Heat Deflection (1.80 MPa) | ISO 75-2 | °C | - | - |
| ISO Tensile Strength | ISO 527-2 | MPa | - | - |
| ISO Flexural Strength | ISO 178 | MPa | - | - |
| ISO Tensile Impact | ISO 8256 | kJ/m ² | - | - |
| ISO Izod Impact | ISO 180 | kJ/m ² | - | - |
| ISO Charpy Impact | ISO 179-1 | kJ/m ² | - | - |