Fiberglass Reinforced Plastics（F.R.P）

PRODUCTNAME	LV-FRP	TYPE	Φ 0.45-5.50mm

PROPERTY	UNIT	PERFORMENCE
Appearance	--	Smooth ,no wrinkle and defect
Diameter tolerance/Ovality	%	±2
Density	g/m ^{3}	2.05-2.15
Tensile strength	Mpa	≥1500
Tensile modulus of elasticity	Gpa	≥50
Elongation at break	%	≤4
Bending strength	Mpa	≥1100
Bending modulus	Gpa	≥50
Minimum bending radius	mm	40×D
Minimum bending radius(40D,20±5℃)		No bur,cracks and break,feel smooth and straight asoriginal

Remark:

The above mentioned data property should only be regarded as a general information of products and not a guarantee. Some of the properties can be tailor made for you.

Address: Room 802, Building A, No.668 Xinzhuan Rd, Shanghai, China
Zip Code: 201612
Tel: 0086-21-64951451
Fax: 0086-21-64951454*807
www.longvision.com.cn
wangwei007@longvision.com.cn