



深圳市久隆旺电子有限公司
 东莞市帝达肯电子有限公司
 材 质 对 照 表

初始磁导率 μ_i	2300±25%	2400±25%	2500±25%	1400±25%	2200±25%	3300±25%	3300±25%	3000±25%	3000±25%	2300±25%	1000±25%	3800±25%	5000±25%	7000±25%	10000±25%	10000±25%	12000±30%	15000±30%
JLW(久隆旺)/DDK(帝达肯)	JP4 JW4	JP44 JW44	JP47 JW47	JP50 JW50	JP90 JW90	JP95 JW95	JP96 JW96	JP96B JW96B	JP97A JW97A	JP95T JW100	JW200	JP4D JW4D	JL5	JL7	JL10	JL10F	JL12	JL15
ACME(越峰)	P4	P41	P48	P51		P45/P47				P52	P61	N42	A05	A07	A10		A121	A151
TDK	PC40	PC44	PC47	PC50	PC90	PC95					PC200		H5B	H5B2	H5C2		H2C4	H5C3
NICERA(尼赛拉)	NC2H	2HM5		5M									NC-5Y	NC-7	NC-10H		12H	15H
EPXOS(西门子)	N67, N87			N49								N45	N30	T35/T37	T38		T42	T46
FERROXCUBE(飞利浦)	3C85,3C90					3C95				3F36	3F46	3B46	3E27	3E25/3E27	3E5		3E6	3E7
DMEGC(东磁)	DMR40	DMR44	DMR47	DRM50	DMR91	DMR95	DMR96	DRM95B	DRM96B			DMR71	DMR5K	DMR7K	DMR10K		DMR12K	DMR15K
TDG(天通)	TP4	TP4A	TP4D	TP5		TPW33							TS5	TS7	TS10/TS10A		TS13	TS15
TOKIN(东京)	BH2	BH1											5H	7H	10H		12H	15H
TOMITA	2F8,2G8												2F1	2E1	2E2		2H2	2H1
SAMWHA(三华)	PL5, PL7	PL-11		PL-F1									SM50	SM70S	SM100			SM150
ISU	PM7	PM11		FM5		PM12						BM30						
JFE(KAWTATETSU)川铁	MB3	MB4	MB4F	MC2		MBT1							MA055	MA070	MA100		MA120	MA150